

Description

Paracril SD3811C is a copolymer of butadiene and acrylonitrile in powder form using calcium carbonate as the partitioning agent.

Packing

This product is commercialized in 50 Lb. Cartons/ 2,400 Lb. / Skid. The weight tolerance on cartons and skids is ± 2 percent.

Uses

It is recommended for use in friction products.

Storage

Store in a dry and ventilated area where it will not be exposed to direct sunlight, extreme temperatures or sources of ignition.

Please consult Paracril SD3811C "Material Safety Data Sheet" (SDS) for more detailed handling and storage information.

Dynasol group only guarantees that SD powder rubber products are hand friable and not free-flowing. To prevent premature agglomeration store below 25°C in low humidity areas.

Chemical properties

Property	Test method	Unit	Value
Total Volatile matter	ASTMD 5668	(%)	1.0 max.
Total Ash	ASTMD 5667	(%)	6 - 8
Bound ACN	INSA	(%)	36.5 - 39.5
Average particle size	INSA	mm	0.12
Mooney viscosity ML 1+4 @ 100C	ASTMD 1646	MU	95 - 135

January, 2018